

ACRYLIC RESIN

Typical Properties

	Value	Units	Test method
Physical			
Melt Flow Rate (230°C /3.8kg)	4.8	g / 10 Min.	ASTM D 1238, 230°C/3.8 kg
Specific Gravity	1.16		ASTM D792
Water Absorption (24hr. Immersion)	0.4	% weight gain	ASTM D-570, Wt gain on 24 hrs water immersion
Mechanical			
Tensile Strength @ Maximum	5,400	psi	ASTM D638
Tensile Elongation @ Break	37	%	ASTM D638
Tensile Modulus	265,000	psi	ASTM D638
Flexural Strength, Maximum (Yield)	8,800	psi	ASTM D790
Flexural Modulus	265,000	psi	ASTM D790
Notched Izod Impact (73°F/23°C)	0.8	ft-lbs. / in	ASTM D256
Rockwell Hardness	35M		ASTM D785
Pencil Hardness	F-2H		ASTM D3363
Thermal			
HDT (0.455 MPa; Annealed) ¹	188 (87)	°F (°C)	ASTM D648
HDT (1.82 MPa; Annealed) ¹	174 (79)	°F (°C)	ASTM D648
Vicat Softening Point (50°C/hr; 10N)	207 (97)	°F (°C)	ASTM D1525
Vicat Softening Point (50°C/hr; 50N)	192 (89)	°F (°C)	ASTM D1525
Thermal Conductivity	1.5	BTU/hr*ft ² *F/in	ASTM C177
Recommended Drying Temp. (Minimum 4 hrs.) ²	180 (82)	°F (°C)	
Optical			
Luminous Transmittance (0.125" / 3.2 mm)	88	%	ASTM D-1003, 0.125" thickness
Haze (0.125" / 3.2 mm)	5	%	ASTM D-1003, 0.125" thickness
UV Screening ³	yes @ 6	mils	

Data given are average values and should not be used for specification purposes

1. Annealing Cycle: 4hrs @ 80°C
2. Recommend drying temperatures assume desiccated air at -40 dew point.
3. Solarkote® acrylic formulations are designed to effectively screen out the high-energy UV wavelength at the noted thickness

The statements, technical information and recommendations obtained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Altuglas International/Arkema expressly disclaims any and all liability. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OR MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be construed as an inducement to infringe any patent, and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations. Altuglas® and Plexiglas® are registered trademarks of Arkema. ©2013 Arkema Inc. All rights reserved.

800-523-1532

ALTUGLAS
INTERNATIONAL
ARKEMA GROUP

solarkote.com

SOLARKOTE
BY ARKEMA

Altuglas International, Arkema Inc., 100 PA Rt. 413, Bristol, PA 19007